

## SECTION 201a – AGGREGATE BASE

### 1. GENERAL

This work shall consist of constructing one or more courses of aggregate or crushed stone (includes crushed concrete) as a base course for the specified pavement section. All materials, equipment and construction shall conform to the latest version of Sections 301, 304, 305 and 307 of the Kansas Department of Transportation (KDOT) Standard Specifications.

Crushed Rock shall comply with the quality requirements for aggregate base construction as specified in Sections 1104 or 1106 of the KDOT Standard Specifications. Adsorption shall not exceed 4%. Graduation of crushed rock shall be as follows:

3/4" Clean

Sieve	1-1/2"	3/4"	#4	#40	#200
% Retained	-	20-60	50-80	80-94	90-98

AB-3

Sieve	1-1/2"	3/4"	#4	#40	#200
% Retained	0-5	5-30	35-60	60-84	80-92

Crushed Concrete: At the Contractor's option, crushed concrete may be used in lieu of crushed rock. The adsorption requirements do not apply. All other quality requirements and gradation shall be the same as that specified for crushed rock.

### 2. MEASUREMENT AND PAYMENT

Unless project limits are changed or there is an error in the plan quantity provided on the Bid Form, there shall be no separate measurement and Payment for this work shall be made at the contract square yard price for "Aggregate Base" of the specified thickness. Payment includes compensation for all labor, equipment and materials necessary to provide a finished product as intended by the Contract Documents.